

The Wilton Method of Cake Decorating

Fondant and Gum Paste

















Swimming in Silver Stunning Syringe Seahorse

Contributed by Barbara Diane Hance




Supplies Needed:

Fine Silver Pin Back, 55mm Nonstick work surface Clear plastic sheet Fine marker Scissors or craft knife Needle Tool Cork Clay 20g Syringe (pink or green tip, cut to 18gauge) Sandpaper 1-3 mm Stone for Eye Roller Tooth Picks 16-20 gm Metal Clay Slats or Cards Paint Brush Dehydrator or hair dryer




Programmable kiln





Step 2. Trace your design onto a clear plastic sheet with a thin line marker. For the clear plastic sheet: Plaid Gallery Glass-Leading Blanks work well. They can be purchased from a craft supply store in the stained glass supply section.








Step 4. Use one tsp. of cork clay; roll it into a snake, tapering at both ends. Leave the center much thicker.

Step 5. Mold the clay using the seahorse body pattern as a guide. Cut excess clay from edges with a knife or scissors. This is a molding process. Shape and cut as you go. Leave the center higher to support the syringe work.





Step 6. Check the "fit" of the pattern to the cork clay body. Align the fins along the body of cork clay to be sure they fit correctly. Trim the cork as needed. Allow to dry overnight.







Step 8. With syringe using the tip cut to approximately 18 gauge, begin to pipe in vertical lines. Then add the horizontal lines (looped scales) using a damp brush to help straighten and attach lines as you go. For

syringe work: lightly touch tip to surface to attach. Lift tip slightly off surface, allowing lines to drop from syringe. Use even pressure. Lines will be rounder and you will have more control of their placement.

"Swimming in Silver" continued



Step 9. Add another layer of vertical stripes on top of the first layer, outlining eyes as you go. A stone can be placed in the wet clay now. It will not be secure. Later a line of syringe will be

used to secure the stone and create definition around the eye area. Allow to dry.

Step 10. Roll 16-20 grams of clay 3 cards thick (.75mm.) Cut out fins with a needle tool and

fins with a needle tool and texture. Texture plates from Art Clay World-Fan shapes make great fin textures. Attach fins to body with paste or a thin line of syringe (remember the side fin). Clean up extra paste with a damp brush as you go.



Step 11. After attaching the fins to the body, use toothpicks to make the fins wavy. Use the syringe to pipe around the eye area, encompassing the stone's edge to secure it in place and add definition to the eye. Brush

mouth with 8 layers of paste forming the "bill." Allow paste to dry between layers.

Step 12. With syringe, outline the front of the seahorse where the fins meet the body to secure the fins in place. Cover the side fin with paste, sprinkle fine silver granules on the fin, and gently press into place. Allow to dry.





Step 13. When dry, turn the seahorse over and outline the entire outside of the body. Pay close attention to the area where the fins are joined to the body and continue around the entire outside of the seahorse. This will

secure all the syringe work, fins, and "frame" to the body. Use a damp brush to push lines into place and fill where necessary.



Step 14. With the syringe, work from the edges to make a secure platform for the pin back pieces (remember the clay area will be hollow after firing). Apply pin back pieces with paste or syringe. Use a damp brush to

clean up pin back and add syringe where needed to secure pin back. Allow to dry.

Step 15. Check to see that pin matches the pin back. Keep in mind that the syringe will shrink in the kiln. Place the pin so that the pivot of the pin is centered, but the pointed tip of the pin is only 1/3 of the way into the pin catch. This ensures



a good fit after the clay is fired and has shrunk.

Step 16. When piece is completely dry, refine as needed. Be sure to clean the surface of the gemstone. Remove any extra clay on the back of the pin that would be unwanted metal after firing. You can use baby wipes or unscented hand wipes as "wet sandpaper" on bone dry clay. Use a light touch, work carefully. This will smooth imperfections in dried clay and clean up unwanted clay from stones, etc. It leaves a nice, smooth finish.

Step 17. Fire the piece. When using cork clay, I set my first ramp speed to 800F and hold for 10 minutes. I set the 2nd ramp temperature to 1200F and hold for 30 minutes. This allows time for the cork clay to burn out, leaving the syringe work intact.

Step 18. Brush the piece with a stainless-steel brush, and tumble if desired.

Step 19. Add pin to back with pliers. Your seahorse is ready to go with you on your lapel, scarf, beach bag, or purse!

Like this project? Contact the artist!

Adornments By Diane

4980 Paul Hance Road

Huntingtown, Md. 20639

410-535-2014

www.adornmentsbydiane.com

E-Mail: Adorn@toadmail.com